

Material : Acetal with 25% Glass Filled (POM)

Spareage Code : ACT-2

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ISO 1183, 23 °C	1.58-1.62	1.60	g/cm ³
Hardness ASTM D 745, 23 °C	M-96	M-96	Scale M
Tensile strength ASTM D 638, 23 °C	151Min	155	mpa
Elongation at break ASTM D 638, 23 °C	3.2Min	3.5	Percentage
Heat Distortion ISO 72 2,Temp at 0.5mpa	---	177	°C