



Manufacturer of Seals for Hydraulic, Pneumatic and Rotary applications

Address: Plot No. A-401/402, Road No. 28, Wagle Estate, Thane - 400 604, India.

T: +91-22-25800972 **F:** +91-22-25827480 **E:** sales@spareage.in **W:** www.spareage.in

Material : Acetal Resin (POM)

Spareage Code : ACT-1

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	1.40-1.44	1.42	g/cm ³
Hardness ASTM D 638, 23 °C	M-94	M-94	Scale M
Tensile strength ASTM D 638, 23 °C	70Min	73	mpa
Elongation at break ASTM D 638, 23 °C	30Min	35	%
Heat Distortion Temp at 0.5mpa	---	158	°C
Operating Temp Range	---	-40 to 140	°C