

Material : Hytrel

Spareage Code : HYT-1

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	1.20-1.24	1.22	g/cm ³
Hardness ASTM D 2240, 23 °C	63	63	Shore D
Hardness ASTM D 2240, 23 °C	97-99	98	Shore A
Tensile strength ASTM D 638, 23 °C	41	44	Mpa
Elongation at break ASTM D 638, 23 °C	420	440	%
Heat Distortion ISO 72 2, Temp at 0.5mpa	---	115	°C