

Material : Phenolic Resin Fabric

Spareage Code : PF-1(CPF)

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ISO-1183, 23 °C	1.37-1.41	1.39	g/cm ³
Hardness ASTM D 785, 23 °C	M-89	M-89	Scale M
Tensile strength ISO 527 1, 23 °C	49Min	51	mpa
Heat Distortion ISO 75 2, Temp at 0.5mpa	---	170	°C